

Slip Test Sample Prep Checklist

1. Correct Size

- ☐ Supply tiles or surface samples of at least 200mm x 200mm.
- ☐ Supply five (5) different specimens of the same material
- ☐ Larger samples (e.g. 500 mm) are preferable where available.

2. Labelling

- ☐ Clearly label each sample with surface type, batch number, and finish.

3. Cleaning

- ☐ Wash samples with pH-neutral detergent and water.
- ☐ Do not alter or polish surfaces beyond normal preparation.

4. Coatings and Sealants

- ☐ Only apply coatings if they are representative of the final installation.
- ☐ Ensure coatings or adhesives have fully cured (typically 7–14 days).

5. Packing and Freight

- ☐ Securely pack samples to prevent edge chipping.
- ☐ Use Zerofal's national courier labels for easy, trackable delivery.